



PERFORMANCE FEATURES

- Excellent cellulosic flame retardant

Product Description

Ulterion® AP An aqueous ammonium polyphosphate solution used to flame-retard cellulosic products such as paper, textiles, and wood. It is particularly suitable for use in fiberboard products due to its' efficiency and process compatibility.

Typical Properties

% Solids	45.0 ± 2.0
PH	7.0
Viscosity (cps)	<100
Gallon Weight	10.9 lbs/gallon
Color	Clear colorless liquid
Specific gravity	1.31 g/ml
Solubility in water	Soluble

Application Methods

Ulterion® AP is typically used to flame-retard cellulosic products due to its efficiency in modifying the burning decomposition of cellulosic materials. The recommended amounts of **Ulterion® AP** to be used in initial evaluations of different cellulosic products are:

Paper	20% solids by weight
Textiles	10-15% solids by weight
Timber	40 kg/m ³ solids

Proper formulation of manufactured wood products can provide for high internal bond strengths and other properties capable of passing existing product requirements. Flame retardant loadings required for a particular application need to be established for each product - wood species vary in flammability, as shown in the USDA data below. The USDA

MARKET USES

- Textile
- Paper
- Wood

printed a reference about the E-84 performance of various wood species, USDA Ag Book #72, "Wood Handbook". A table in that book reported as follows:

<u>Species</u>	<u>E-84 Fame Spread</u>
White Spruce	65
Douglas fir	70-100
Lodgepole Pine	65-110
Red Oak	100

Typical flame-retardant loadings to achieve various international burn test ratings are summarized below for medium density fiberboard (MDF) products produced from pin species. Applicable flame-retardant loadings require for other species and products may vary.

Typical MDF Product Analysis

Burn Test	Typical product analysis % Flame-retardant	Typical on dry fiber, % Flame-Retardant
NFP 92-501	3.1	3.8
MI, Face Core	1.9	2.2
UL 726 Class	2.3	2.8
I, Face Core	1.3	1.5
BS 476 Part	1.6	
7, Face Core	1.3	1.5

A typical Formulation may include 5-6% binder, 0.1-1% sizing agents (paraffin), 0.05% dyes, and other chemicals. The product analysis above includes 5-6% atmospheric moisture.

The information contained herein is thought to be accurate in all aspects; however, the applications for these products mentioned are presented without guarantee or responsibility as to the suitability of our products whether used singly or in combination with other products. Nothing herein is to be taken as a license to operate under or as a recommendation to infringe any patents. The products are sold without warranty, expressed or implied, and are purchased at buyer's risk.



Handling / Storage Stability

Keep from freezing. Store in cool, dry area i.e., 70-80°F. Keep away from high heat to retain a six-month shelf life.

Product Safety

Ulterion® AP is a non-hazardous liquid. As with all industrial chemicals, basic handling precautions are recommended. Avoid skin contact. Avoid mist inhalation or eye contact. Wear protective clothing and goggles if there is a chance of exposure. Prolonged skin contact may produce dermal reactions, especially under wet conditions.

When considering the use of **Ulterion®** brand products, please refer to the latest Safety Data Sheets (SDS). If a SDS for this product is required, please contact your **Jain Chem Representative**.

Jain Chem, Ltd.
200 Tanner Drive
Taylors, SC 29687
Phone: (864) 609-0910
Fax: (864) 331-4264
www.jainchem.com
www.ulterion.com

The information contained herein is thought to be accurate in all aspects; however, the applications for these products mentioned are presented without guarantee or responsibility as to the suitability of our products whether used singly or in combination with other products. Nothing herein is to be taken as a license to operate under or as a recommendation to infringe any patents. The products are sold without warranty, expressed or implied, and are purchased at buyer's risk.

ULTERION
taking solutions farther.™